

Future Challenges in BGA/CSP Rework
Patrick McCall PACE Incorporated
Laurel, Maryland, USA

Introduction:

Area array and other components that do not have accessible leads once mounted on a printed circuit board (PCB) are extremely common in today's electronics. The ability to remove and replace them by the service industry is a critical competency. These types of components have gained significant acceptance and with each generation of smaller and more powerful products. Area arrays bring with them special process considerations when rework and repair is required. These include higher levels of process control, more precise control/application of heat, lead free solder considerations, and advances in component construction.

Over the last few years, the cost of the specialized equipment to handle these types of components has come down to where it now very affordable to independent service centers. The procedure/process for reworking area arrays is often very different from reworking standard surface mount components. It is a longer process and of course, there is more opportunity for mistakes. In general, the typical procedure includes the following steps.

Removal of Old Package and Site Preparation:

Removal of old package and Site Preparation: When removing packages from PCBs, the approach should be driven by the reason for the removal and whether or not the component will be reused. When removing a package because it has failed, a removal profile may be developed that uses faster ramp rates and shorter times because we are not concerned about the survivability package. However, when a device is intended to be reused, a removal profile similar to the installation profile with slow and even heating or the installation profile itself should be used. This is also the case when dealing with PCBs and packages that are made from materials that must adhere to ramp rate guidelines.

Regardless of the approach, proper pre-heating and thorough PCB warming is critical to the success. Removing packages by only applying heat from the top should be avoided. This technique can easily result in pads being damaged or lifted. The amount of heat required to bring the solder balls to melting temperature through topical application will often overheat the rework site and will usually exceed recommended heating ramps. It also causes significant temperature differences between the top and bottom of the device and PCB, which can cause twisting, flexing and damage to micro-vias and other delicate circuitry as well as delamination of the package.

Package delamination is a common problem that is becoming more common as layers of different materials are being used in the component's construction.

It is extremely important that all the solder joints under the package are liquidus before lifting the package from the PCB. Rework equipment that utilize devices to automatically lift a package after the removal profile is completed are common and generally work well. However, if they are used, the removal profile must be validated through the use of thermocouples to ensure proper temperatures are reached. Should one or a few solder joints not reach solder melt temperatures and the automated head lifts up, pads can and will be pulled off the PCB. Pads and traces for MEPs are often very delicate and cannot be repaired.

Another consideration when vacuum cups are used inside of the nozzle is that the vacuum cups shield a portion of the component resulting in uneven heating. Typically, this is not a major issue in larger packages because they have longer heating cycles that allow the entire package to reach a homogenous temperature. Because MEPs have shorter heating cycles, are thinner and have different materials compositions than their standard cousins, they are more likely to develop "cool spots" under the vacuum cup which can result in non-liquidus solder joints. To avoid pad damage, the duration or dwell time of the reflow phase can be increased. The use of thermocouples when developing and validating profiles should become standard practice in every rework facility.

Once a package has been removed, the rework site must be properly prepared for the next installation. Excess solder on the land patterns with pads larger than .8 mm can usually be removed using one of a variety of conductive desoldering tools available. Other techniques include the use of solder wick or the use of hot gas heating. Removing excess solder from land sites with pads less than .5 mm requires a very delicate hand. If conductive desoldering tools are selected, a light touch and low temperatures must be used. Temperatures over 200 degrees C combined with pressure can easily damage pads or the solder mask.

In general, PCBs that have vias through them are not good candidates for purely conductive desoldering techniques. While the desoldering tip is moved across the land pattern, the vias can become filled with solder. These are not easy to clean out and attempting to do so can result in damage to the via, solder mask or the PCB.

Hot gas removal systems or conductive systems incorporating hot gas assisted heating that use Teflon or stainless steel tips at low temperatures and are preferred. The use of solder wick is generally not recommended for MEP land preparation, unless it is used in the hands of a very skilled technician.

"Bumping" of the lands is another technique used to remove excess solder or to add additional solder to the rework site by using a soldering iron tip to reflow the solder on the pads and level it as well. This technique is quite common when placing leaded devices. Typically, flux is applied to the land site, and then a tinned tip is drawn across the array. The surface tension of the solder is relied upon to control the volume of solder left behind on the pad.

If pads are bumped, they will be rounded, not flat. Therefore, a sticky or gel flux must be used in to hold the package in position. During Soak when the flux is activated and driven off, the package will usually move and can easily become misregistered to the land array. While bumping can work fairly well on standard packages, it is not recommended for MEPs land site preparation. If bumping is used on MEPs, a number of issues must be considered. The amount of solder involved with a MEPs interconnect is very small. Using old solder can result in poor quality joints and adding too much can result in bridging. Often, MEPs pads are so small in diameter, that the surface tension of the solder on the tip will just pull the solder over the pad, leaving just a thin covering behind. Additionally, drawing a hot iron tip over the MEPs array can damage and lift pads. The most significant issue is that the solder bumps will not be perfectly

level. When installing packages with ball diameters as small as .1 mm, it doesn't take much to end up with an unlevel package, which can result in "opens".

Once the excess solder has been removed, it is important to properly clean the PCB. The pads must be clean and free from old solder and flux residue before proceeding with the replacement of the package. When installing MEPs, proper cleaning is just as important to the process as the installation profile. Shorter reflow cycles, small amounts of flux used for installation, coupled with the small volumes of solder present in each joint does not make for a forgiving reflow configuration.

Placement:

Placing standard packages is relatively easy and can be accomplished with commonly available techniques. Placement by hand is a viable option for these packages by using a template or the silkscreen around the land pattern as a guide. A vision overlay system (VOS) can be used to ensure proper alignment and is usually preferred by most operators. Typically, a minimum magnification of 35X is required to ensure proper alignment. A placement precision of .1 to .2 mm in the Z travel is usually adequate.

To place MEPs successfully a VOS must be used. A minimum magnification of 80x is required and quite often 100x is needed to accurately align flip chips. Placement precision in the Z travel should be 50 microns or less. When placing flip chips, 25 microns is needed.

The level of precision required for placement in the Z travel mechanism is directly related to the diameter of the solder ball itself. Precision rating requirements should be calculated by using the smallest solder ball diameter that will be reworked. To ensure proper installation, the solder ball must cover at least 50% of the pad on the PCB. In other words, when the device is placed on the PCB the accuracy must be at least 50% in order to take advantage of the self-aligning properties of array packages. See Figure 1. Keep in mind that the more accuracy that can be achieved, the better the result. Packages that are less than 50% aligned can actually migrate one row of the array, which results in a faulty installation.





Figure 1

VOSs are readily available with many different options. Typically, a VOS is comprised of a prism that is used to collect two images, one from above and one from below. The images are projected onto a series of mirrors where they are then projected into the lens of a camera. The images are displayed on some type of video monitor and appear as two separate images overlaid on one another. Either the component or the board is repositioned until the ball and land array patterns match exactly. See Figure 2.



CSP not aligned CSP aligned
Figure 2.

Most VOSs used today also have a “split vision” capability, which allows the viewer to see only two opposite corners of the images at a higher magnification. This is valuable when placing devices that have hundreds of solder balls. To attempt to align more than 300 data points is difficult. If the images can be “split” and magnified, the user can simply align two opposite corners of the package while focusing on less than 100 points of data. See Figure 3.




Figure 3: Full view and Split Screen View

Proper care and maintenance of the VOS is important to placement success. Calibration checks should be performed at regular intervals as indicated by the manufacturer. When adjustment is required, it should only be completed by qualified individuals.

Flux/Paste Application:

Flux must be used to have successful package installation. It may be used by itself or it may be combined with solder in the form of solder paste. Applying the proper amount of flux to the rework site is critical. Too little flux and the solder will not flow correctly, too much flux and out-gassing can occur which result in voids within the solder joint or flux will be left over which can cause resistivity problems as well as have corrosive effects on the solder joint after reflow. There are a variety of methods for applying flux. Some of the methods are to use a brush or pen applicator, to use a piston driven mechanism to dispense a gel or sticky flux, and to use a flux applicator tool.

When applying flux to area array packages, the ideal amount of flux to apply is enough to cover 1/3 of the solder ball. This ensures that enough flux is present to clean and remove oxides while eliminating the potential for out-gassing and excessive flux being left behind. With the introduction of gel flux, applying precise amounts of flux to balls can be accomplished and repeated consistently.

Solder paste should always be used when:

- Solder balls on the bottom of the package are made from 90/10 solder.
- PCBs have bare copper pads on them,
- The package contains an elastomer layer for CTE differences,
- It is critical to have the same joint geometry as the production assembly and solder paste was used in initial production,
- No clean flux can not be used,
- A specification exists for the joint stand-off height for function or cleaning.

Solder paste can be applied using a variety of techniques. Some of the more common techniques include using spot stencils to apply solder paste to the PCB, using component stencils

to apply solder paste to the component, and using dispensing equipment to apply dots of solder paste to each individual pad.

Solder paste with ball sizes of #4 should be used for small pad printing. When applying solder paste to standard packages, typically, a paste thickness of .17 to .23 mm is desired. When using solder paste for MEPs, a paste thickness of .1mm to .16mm is desired.

Stencil aperture shape is also an important consideration. Typically, stencils with apertures larger than .2 mm are round and lend themselves to good release. Apertures in stencils designed for paste deposits smaller than .2 mm are often diamond shaped. The diamond shape allows the solder paste to release from the stencil easier than a circular one.

The Impact of Bottom-Side Heating:

Bottom side heating is usually associated with the “pre-heat” phase of a profile. However, bottom side heating is as important in Soak and Reflow phases if the installation is to be successful while exposing the PCB and package to a minimal amount of thermal stress.

In the “Pre-heat” phase, bottom side heating ensures homogenous temperatures across the board. This keeps the PCB from warping, twisting, or flexing, during the process, which is essential for maintaining planarity of the installation site. Heat application from the bottom of the PCB during the “pre-heat” phase is also used to warm the entire PCB so that heat is not drawn away from the installation site during the rest of the process.

During “Soak”, the bottom side heater should continue to operate while a relatively small amount of heat is added from the top heater. The combination of top and bottom side heat application allows the installation site and package to reach a temperature of between 140 and 160 degrees C and to stabilize. The stabilization should be maintained for 40 to 60 seconds, allowing the flux to activate and driving off any volatiles in the flux. This is important as it eliminates the potential for out-gassing and prepares the package and PCB for reflow.

During “Reflow”, heat is usually actively applied from the top heater. Top heaters generally operate between temperatures of 200 and 350 degrees C. Obviously, this can place a lot of thermal stress on the top of the package. It is important to apply heat slowly and evenly so the entire package warms to reflow temperature uniformly. Temperature differences across a package of as little as 5 to 10 degrees C can cause damage.

The set temperature of the bottom heater can be maintained or increased during reflow. Increasing the temperature by as little as 15 degrees C during reflow will have a dramatic impact on the package profile. One of the many benefits of adding additional heat from the bottom or “Spiking” during the reflow phase is that lower temperatures can be applied from the top.

Installations should always be achieved with the lowest temperatures possible. This ensures the safety of the package as well as PCB. Additionally, by subjecting the package to lower temperatures, there is less chance for temperature overshooting which can result in significant temperature variations between the top of the package, bottom of the package, the solder joint and PCB. See Figures 4 and 5.




Figure 4.




Figure 5.

As can be seen in Figures 4 and 5, reflow was achieved successfully in both scenarios. However, in Figure 4 the temperature variation between the top of the package and the solder ball is significant enough to damage the package. Refer to Table 1 for spike impact analysis.

Table 1

	No Spike (°C)	Spike (°C)
Max reflow temp (top of Device)	218.5	205.4
Max temp of solder ball	200.2	196.1
Max temp of PCB under Device	201.4	197.5
Delta between top of Device and Solder ball @ max reflow temp	18.3	9.3
Delta between Bottom of PCB and solder ball @ max temp	1.2	1.4
Delta between Top of Device and Bottom of PCB @ max temp	17.1	7.9

By controlling the application of heat from the top and bottom of the installation site, more even heating can be achieved. This can be seen in lower temperature variances between the top and bottom of the package and between solder balls located on the outer edge and in the middle of the array pattern.

Heating Process Considerations:

While standard BGAs and MEPs look similar in design, they are actually quite different and demand different profile configurations when it comes to installation and removal profiles. Physically, they differ in several areas: materials, dimension, mass, and tolerances to temperature. In general, profiles used to install MEPs are shorter than profiles for standard packages. Also, lower temperatures can and should be used when installing MEPs. Because the MEPs package is the size of the silicon die, or slightly larger, there is no significant encapsulation for protection, heat is applied/transferred directly to the silicon.

The smaller mass of the MEP solder balls, coupled with a very thin package allows heat to be transferred through the component very quickly. When standard BGAs are installed, heat must be driven through and around the package, which requires a longer heat application period. Therefore, if a profile for a standard package is used on a MEP, the component will become super heated which is something that must be avoided.

As was mentioned previously, vacuum cups in the nozzle can affect profile results. To demonstrate their effect, a micro BGA 46 was installed twice on a PCB from a cellular phone using the same profile parameters. A hole was drilled through the center of a pad and a thermocouple was installed flush with the top of the PCB, contacting a solder ball. The only difference between the two trials was the addition of the vacuum cup. See Figure 6.




Figure 6

The effects of the vacuum cup is dramatic:

1. Soak and Reflow ramp rates are slower
2. Final Soak Temp is lower
3. Heating continued beyond the reflow phase
4. Cooling was inhibited
5. The solder balls did not reflow.

In this case, the vacuum cup used was round so the edges and corners of the micro BGA were exposed to more heat than the portion of the package under the vacuum cup. This results in higher temperature variations across the entire package.

There are many methods for applying heat as well as different methods to monitor and control it. Arguments can be made for all. Heaters used in area array rework equipment are almost always controlled through closed loop structures. This means that the heater is cycled on and off based on the condition of the thermal sensor. In many cases the variation between set temperatures and actual temperatures between area array rework equipment is due to the position of the sensors.

Sensor placement can dramatically affect the result of set temperatures, which is why a valid profile configuration developed on one rework machine does not usually successfully transfer to another. Ultimately the set values on a particular machine are not critical. What is critical, however, is the thermal environment those set temperatures create around the package and PCB. Profiles should always be created and validated using feedback from thermocouples.

Many systems allow profile settings to be adjusted while a profile cycle is running. Usually a PCB will be populated with thermocouples in a number of locations. It is good practice to place thermocouples:

- on the top of the device,
- on at least one solder ball, 2 is better (inner and outer ball), and
- on the bottom-side of the PCB, both, directly under the rework site and away from the rework site.

Positioning thermocouples in these locations allows:

- monitoring of temperature variations between the top and bottom of the package,
- monitoring of temperature variations between the middle and outer edge of the package, as well as
- monitoring of the thermal environment the solder balls are exposed to.

Monitoring the temperature directly below the rework site is important as PCBs can be subjected to too much heat, as can packages. This can cause damage to circuitry, micro vias, and delamination of the PCB itself. The purpose of the thermocouple on the bottom of the PCB away from the rework site is to ensure the entire board is warmed properly and is not exposed to high temperatures in one location, under the rework site.

Profiling can be accomplished using a site containing a previously installed package, or by performing an actual installation. Either method can be used to develop a reliable profile. However, there are some issues to be aware of with each.

If using a site where a package is already installed, the placement of the thermocouples is important. They must have contact with the existing solder joints. This is best accomplished by drilling through the bottom of the board into a solder joint and affixing the thermocouple with an adhesive or other means to secure it. Affixing a thermocouple to the top of the package that is already soldered is easier in most cases, especially when MEPs are involved.

When developing profiles through an actual installation, it is important to make sure the solder balls are touching the thermocouples through out the entire process. Should a thermocouple lose contact with the solder balls, bad data will be collected. Additionally, it is often difficult to affix a thermocouple to the top of a loose package and successfully maintain contact with the PCB during the process.

Feedback from the thermocouples will assist the operator in adjusting the time and temperature parameters. In general, the following guidelines should be adhered to when developing profiles.

Ramp and Maximum Temperatures

Acceptable ramp rates and maximum temperatures can be obtained from the package manufacturer. It is wise to select a maximum temperature that allows a margin of safety to the manufacturer's specification.

Pre-Heat

1. If a "step profile" is desired, the top of the PCB should reach a stable temperature of 95 to 105 °C during pre-heat. Stability is the main goal here. When plotting a curve, the trace should level off at this temperature.
2. If a linear slope is desired, preheat is merged with the soak phase. In this method, the package and PCB are warmed at a constant rate (the ramp rate usually 1 to 3 °C/s) until the desired soak temperature is reached.

Soak

Soak is a critical step in the process. It is used to activate the flux and to drive off volatiles and excess flux. It is important that a soak temperature between 145 and 165 °C be reached. Ideally, a relatively stable temperature should be maintained for 40 to 60 seconds. This should be extended if liquid flux is brushed on to the PCB or when installing a large package. Soak also allows the entire package and PCB to come to a uniform temperature. If the entire package and PCB are the same temperature the rate of temperature increase in response to the additional application of heat during reflow will be the same throughout. This allows for uniform ramping across the entire package.

Reflow

Reflow is the second to last phase in the cycle. During this phase the solder balls reach solder melt and form the joint between the package and the pads. It is critical that all areas of the array reach solder melt together and that all balls are liquidus for at least 20 to 45 seconds. Generally, Reflow for MEPs will be a shorter phase than for standard packages. Additionally, lower temperatures can be used for MEPs as they are thinner and have less mass. When developing profiles for MEPs it is very important to not apply too much heat.

The type of solder used in the solder balls is variable that can greatly impact the profile of a component. It is likely that lead free solders will be common over the next 1 to 3 years. The reflow range for is defined by: 1) the maximum temperature a component can be exposed to (usually the max minus 10 degrees C) and 2) the melting temperature of solder. Typically, the range for reflow, when using 63/37 solder is between 195 and 225 degrees C. This is a fairly wide and forgiving range. When lead free solders are used, the reflow range is between 210 and 225 degrees C. This is a much tighter window so slow, even uniform heating is required so the window is overshot. Again, the use of thermocouples to validate profiles results is critical.

Another variable that must be taken into account when profiling is whether or not the component has a heat spreader or not. When heat spreaders are present, the requirement for slow and even heating is more stringent. The greater the variety of materials present in a given component, the greater the likelihood of delamination.

Cool Down

Cool down is the last phase of the cycle. It is used to bring the temperature of the package, solder joints, and PCB under the package below solder melt temperatures. Cooling should be controlled and a good rule of thumb is to use the same rate for cool down as for ramp up. If the ramp rate were 2 °C/s increase, the cool down rate would be a temperature decrease of 2 °C/s.

Once a profile has been initially defined, it is important to re-run the profile with the determined parameters in a static (non-changing) environment to ensure the results are valid.

Inspection

There are several options for inspection BGAs and MEPs after installation. The most common type utilizes some sort of X-ray imaging device.

X-Ray systems

Generally, X rays are emitted through the component to an X-Ray detector, which generates a black and white image. The B/W image is then displayed on a monitor of some type. Usually, images are real time and can be stored using video equipment or PC software. The level of blackness on the image corresponds with the thickness of the material and/or the density of a material. See Figure 7.





Figure 7

X ray systems can be used to view a wide range of components. Examples of what images look like for the most common packages follow:

1. Plastic BGA Package Parameters


- Plastic Package
- Collapsible Balls
- Most Common BGA Package
- Can Inspect With Any Low-Power X-ray System



2. Super BGA Package Parameters




PBGA with copper heat spreader
 Collapsible Balls
 Stiff Package
 Less Common
 Need moderate X-ray power to inspect




3. Ceramic BGA Package Parameters

Ceramic Substrate
 Non-collapsible Balls (90/10 solder)
 Stiff Package
 Optional heat spreaders (aluminum)
 Common (2nd after PBGA)




4. Tab BGA Package Parameters

Copper frame and stiffener
 Non-collapsible Balls
 Integrated copper heat sink
 Less Common




5. Micro BGA/CP Package Parameters

Plastic/ Thin metal Package
 Collapsible Balls
 Less Common BGA Package
 Requires high magnification



6. Flip Chip Package Parameters

Silicon Die
 Collapsible Bumps
 Less Common BGA Package
 Package is Encapsulated After Attachment
 Requires high magnification



7. TI DSP Package Parameters

New BGA package.
 Dense metal heat sink
 Requires voltage of 70 Kv or higher.



X-Ray systems range in power from between 35 and 90 Kv. Some have adjustable power and others are fixed. One common technique technicians evaluating installations is "voltage blooming". When the X-ray power is turned up, voids appear to be larger than they really are. Figure 8 shows the same solder joints viewed at 50 and 70 Kv.





Image at 50 Kv

Image at 70Kv


Figure 8.

As a rule of thumb, you should only use as much power as needed to view the bonding wires in the component. If too much power is used, the bonding wires will be washed out of the image and voltage blooming is very likely to occur.

The other feature that separates systems apart is how the X-rays pass through the work-piece, either straight down or using variable angle viewing. Systems that have variable angle viewing do so by either rotating the x-ray head around the work-piece or by rotating the PCB under the head. Generally, variable angle viewing systems cost significantly more. In some cases, they are preferred as they often have software that will complete the analysis of the installation. However, just as many types of defects can be viewed using a straight down viewing systems but the training requirement for operators is higher as they are required to identify solder joint “signatures” and infer process problems. Straight down viewing systems can also be used on the bench-top, making them more convenient for rework technicians. The types of defects that can be identified are as follows:


1. Bridging

- May be due to excessive paste
- Solder splattering due to non-optimized reflow conditions.
- Solder balls too large for the gap between the two substrates.




Insufficient Reflow

- Under sized ball bonds (Not Collapsed)
- If package was misplaced the ball shape will be elliptical
- Bond distribution is not consistent
- Possible “Open” joint




2. Missing Solder Balls

- Missing balls can occur in the manufacturing process.
- Usually due to mishandling.
- Migration to another pad or bond that appears unusually large



3. Voids


- Solder voids are often the result of moisture in the BGA package or a problem with the solder paste. A recent article by Motorola indicates that balls that containing voids up to 24% in area



- were more reliable than those package without voids.
- Voids are a process indicator and are not necessarily a defect unless excessively large.


4. Cold Solder

- Cold solder is signified by a jagged irregular edge around the perimeter of the solder ball and is caused by inadequate wetting. Note that in this image only some of the balls show this signature.
- Possible “open” joint



5. Warpage

- Solder balls in the center of the package are oversized due to delamination and compression under die area.
- Possible “Open” joints around the outside edge of the package.



It is important to note that once defects are identified, improvements/changes must be made to the installation process. The defects identified above are all indicative of process issues that can be controlled through proper storage, handling and heating of area array components and PCBs. X-ray inspection is not a substitution for proper process. It is to be used as an auditing tool to assist in the development of profiles and procedures, which will ensure successful reflow time and time again.

Conclusions:

The use of MEPs will continue to expand and the ability to rework them will become a critical competency. They offer similar benefits as standard BGA packages but at a much smaller size. During rework, it is extremely important to prepare the land array properly by removing excess solder and proper cleaning. Placing MEPs on the PCB is a similar process to placing standard BGAs. However, it can require more delicate and precise equipment. The proper application of flux and paste (if used) is also critical to the success of the installation. Having the right amount is the key, too much or too little can lead to more rework.

Bottom side heating is one of the keys to success. When used properly, reflow can be achieved at lower temperatures while exposing the package and PCB to less thermal stress. Additionally, increasing the temperature of the bottom heater during reflow allows for a stable and uniform reflow. While it can be compensated for, it is important to be aware that the results of the profile can be affected if any additional mass is present inside of the nozzle or if anything is contacting the package during reflow. The use of thermocouples is paramount when developing and validating profiles. Using multiple thermocouples at multiple locations is preferred.

Guidelines for profile development exist and should be used. Manufacturers specifications should also be adhered to and it is good practice to add a margin of safety to maximum temperature and ramp rate specifications. Profiles used for standard BGA packages will not

transfer directly to MEPS. However, they can be used as starting points in developing the perfect profile.

Inspection systems are a tool and should be used in the development process and to verify reflow conditions every so often. When defects are found, procedures, profiles, and proper equipment operation should be audited. Understanding how to read an X-ray image from a straight down viewing system allows the operator to identify the most common defects without having to spend significant dollars on equipment.

References:

1. Kevin Towle, Line Configuration for Today's Highly Complex Manufacturing, SMT Magazine, 11/98
2. Japan Printed Circuit Association, Report on the Technology Road Map for Advanced System Integration and Packaging, 1998
3. Mike Bixenman and Trelant Fang, Wafer Solder Bumping, Advanced Packaging, 6/99
4. Mike Sauer and Kristina Bergman, Rework & Repair, SMT Magazine, 7/99
5. Paul Wood, New Considerations in CSP Rework, Circuits Assembly, 7/99
6. Mei Wang, Kazu Nakajima, et al, Investigation of the Printing Process for CSP Assembly, SMTA 1999 Conference Proceedings.